

Technical Information



Product name	:	MoTip Camouflage Lacquer			
Colour	:	RAL 1001	RAL 6014	RAL 6031	Grey
Article number	:	04201	04202	04203	04204
Colour	:	RAL 8027	RAL 9021	RAL6006	
Article number	:	04205	04206	04207	
Supplier / Producer	:	MOTIP DUPLI B.V.			
		Wolframweg 2			
		NL-8471 XC WOLVEGA			
		Telephone number	+31 561 – 69 44 00		
		Telefax number	+31 561 – 69 44 31		

Product description

High quality camouflage lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone, textile and various types of plastic.

Product characteristics

Excellent coverage and filling property
Lasting colour and gloss
Scratch free and shock proof
Resistant to petrol, chemicals and weather influences
Corrosion preventive
Excellent adhesion

Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Alkyd resin
VOC-content	:	Approximately 83% w/w
Solid content	:	Approximately 17% w/w
Gloss	:	Mat <5 at an angle of 60°
Coverage	:	1,25 to 1,75 m ²
Dust dry	:	After 10 to 20 minutes
Tack free	:	After approximately 45 minutes
Hardened/re-sprayable	:	After 16 hours
Heat resistant	:	To 110°C



Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

Even when the lacquer has hardened, do not treat with acrylic lacquer or nitro-cellulose lacquer.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.