



Product name	:	MoTip RAL Lacquer	
Colour	:	Flame Red RAL3000	Enzian Blue RAL5010
Article number	:	04105	04106
Colour	:	Yellow Green RAL6018	Zinc Yellow RAL1018
Article number	:	04107	04108
Supplier / Producer	:	MOTIP DUPLI B.V. Wolframweg 2 NL-8471 XC WOLVEGA	
		Telephone number	+31 561 – 69 44 00
		Telefax number	+31 561 – 69 44 31

Product description

High quality, fast-drying lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

Product characteristics

Fast drying
Good coverage
Lasting gloss
Non-fading and UV resistant
Good surface hardness
Resistant to petrol, chemicals and weather influences
Wear resistant and scratch free
Excellent adhesion

Physical and Chemical Characteristics

Contents	:	500 ml
Base	:	Acrylic resin
VOC-content	:	Approximately 91% w/w
Solid Content	:	Approximately 9% w/w
Gloss	:	High gloss
Coverage	:	1,5 to 2 m ²
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 2 hours
Heat resistant	:	To 110°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).

Treat

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.