

TEKNOS

SILOKSAN

SILOKSAN FACADE

Silicone emulsion paint

SILOKSAN FACADE is a water-borne, full-matt facade and brick house paint for mineral surfaces. The paint is very permeable and water-repellent.

Use: New and previously painted facades outdoors, e.g. concrete, plaster, mineral boards and brick surfaces: burnt brick and lime-sand brick.

SILOKSAN FACADE silicone emulsion paint is easy to apply with roller or spray. Its binder composition prevents the paint from becoming brittle by the action of UV-light or heat. As SILOKSAN FACADE is water-repellent it keeps clean even in urban climate, and acid gases in the atmosphere do not corrode it. SILOKSAN FACADE can be overcoated the same day. It does not require any separate priming coat on most surfaces, when SILOKSAN GEL is added into the paint for the first coat.



TECHNICAL DATA

| Certificates, approvals and | CE marking, Finnish Key Flag |
|-----------------------------------|--|
| | CE marking, Finnish Rey Flag |
| classification | |
| Fields of application | Outdoor wall, Socle |
| Recommended substrate | Cement plaster, Clay brick, Concrete, Lime sand brick, Mineral boards |
| Solids | Approx. 36% by volume |
| Volatile organic compound (VOC) | EU VOC limit value (kat A/c): 40 g/l. The product's VOC: max. 40 g/l. |
| Practical spreading rate | 4 - 6 m²/l. |
| Colours | Base paints 1 (white) and 3, which can be tinted to obtain most of the shades in |
| | Exterior Colour Card. |
| Tinting system | Teknomix |
| Gloss (60°) | Full-matt |
| Thinner | Water. |
| Density | Approx. 1.5 g/ml |
| Storage | Must not freeze. |
| Packaging | Base paints 1 and 3: 2.7 l, 9 l, 18 l. |
| | Availability varies by country. |
| Water-vapour permeability (EN ISO | s _d < 0,14 m |
| 7783) | |



DIRECTION FOR USE

Surface preparation

NEW CONCRETE ELEMENT OR CAST SURFACES:

New concrete element or cast surfaces can be painted with SILOKSAN FACADE Silicone emulsion paint when a minimum of one month has passed after the casting, the surface is completely bound and no longer wet or matt moist. In measurements the moisture values of the concrete must be under 97% as relative humidity (RH) or 4 % as per cent by weight. It is recommended that new plaster surfaces are coated only after a hardening time of 6 – 8 weeks.

Remove all dirt from the surfaces by cleaning with high pressure washer. When needed, add sand to the washing water or use a steel brush or similar in order to achieve sufficient surface profile (e.g. mould-cast surfaces). NOTE! When painting concrete elements take care of removing the laitance before painting. When preparing and painting substrates containing asbestos, regulations given by authorities must be followed.

BRICK SURFACES AND MINERAL BOARDS:

Remove loose matter, dirt and dust by e.g. hot water wash or RENSA FACADE facade cleaner according to the instructions. Allow the surface to dry thoroughly before painting.

PREVIOUSLY PAINTED OR PLASTERED SURFACES:

Remove flaking and poorly adherent or pulverized (e.g. lime wash) paint coats from previously painted surfaces. The method to be used is chosen depending on the strength of the substrate and the type of the paint to be removed (e.g. wire-brushing, hot pressurized-water cleaning or water-sand cleaning). Remove also poorly adherent, brittle plaster and concrete surfaces. Check the condition of the concrete seams and repair where required.

If concrete constructions have cracks by the reinforcement bars, these cracks are to be opened by e.g. chipping or with a grinding machine. After this the concrete is roughened, if required. Clean all rust from the exposed steel bars and protect them with e.g. a coat of INERTA MASTIC epoxy coating. Use appropriate mortar, on plaster surfaces repair mortar, to repair the opened cracks and dents. Finish the repaired areas carefully and let them harden before they are painted. Stir thoroughly before use. Prime clean and solid mineral and brick surfaces with SILOKSAN FACADE Silicone Emulsion Paint with an addition of SILOKSAN GEL (9 : 1). For priming the paint may be diluted by 5 % with water. This priming can also be used for previously painted surfaces. Airless spraying, Brush, Roller Suitable airless nozzle size 0.017 - 0.021".

Priming

Application method



| Application conditions | During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. |
|------------------------------------|---|
| Drying time | +23°C / 50% RH |
| - dust free | 30 min |
| - overcoatable | 2 - 3 h |
| | The drying process will be slower in cold and/or damp. |
| Top coating and suitable top coats | Top coating with undiluted SILOKSAN FACADE silicone emulsion paint. Reserve a sufficient amount of paint of the same batch for each uniform surface to prevent possible colour differences. If different batches must be used, possible seams between the batches are placed as inconspicuously as possible and are painted with a mixture of paint from both batches (e.g. 1 : 1). |
| Resistance | Weather resistance: Very good. |
| Cleaning | Warm water and RENSA BRUSH brush cleaner. Wash the equipment immediately after use. |

HEALTH AND SAFETY

| Safety and precaution measures | See safety data sheet. |
|--------------------------------|------------------------|
|--------------------------------|------------------------|



| CE | | | | |
|---|---|--|--|--|
| 0809 | | | | |
| Teknos Oy, Takkatie 3, P.O. Box 107, FI-00371 Helsinki, Finland. | | | | |
| 13 | | | | |
| Declaration of Performance No. 0018 | | | | |
| 0809-CPR-1063 | | | | |
| EN 1504-2:2004 | | | | |
| (tested in the following coating systems: SILOKSAN FACADE silicone emulsion paint with the addition of SILOKSAN GEL | | | | |
| SILOKSAN PRIMER, priming + SILOKSAN FACADE silicone emulsion paint) | | | | |
| Surface protection products – Coatings | | | | |
| Moisture control (2.2) | | | | |
| Increasing resistivity (8.2) | | | | |
| Water vapour permeability | Class I: s _D < 5 m | | | |
| Capillary absorption and permeability to water | Requirement: w < 0,1 kg/m²h ^{0,5} | | | |
| Adhesion strength by pull of test | Requirement: Rigid system without trafficking: ≥ 1,0 (0,7) N/mm² | | | |
| Dangerous substances | See safety data sheet | | | |

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.